

FISCHER PLASTIK

Gesellschaft m.b.H.

A-4511 Allhaming 101, Tel.:07227 7181, Fax: 07227 718122

Polyäthylen, die
umweltfreundliche
Verpackung –
recyclbar

Herstellung von Folien, Schläuchen, Säcken, Tragtaschen aus HD-, LD-Polyäthylen
unbedruckt und bedruckt, Automatenrollen, Putzereischläuche, Schrumpffolien,

FirmenbuchNr.: FN 119762
UID-Nr.: ATU 22518309

Technical Data Sheet

Product: lbh0-00-040-060-03-r0-00 HDPE-Bag 400x600mm/25µm 24795

Properties (standard values)		
Material		PE
Melt Index MFR 190/21,6	g/10 min	7,0-9,0
Density (23 °C)	g/cm ³	0,94-0,955
Vicat Softening Temperature	°C	128
Additives		yes
Colour		no
Food save	EC-10/2011	yes

We confirm that the a.m. product fulfils the requirements on materials used for articles intended to come into contact with food as described in:

- Regulation (EC) No 10/211
- Regulation (EC) 2023/2006
- Directive 94/62/EC

Migration values:

Material complies with the requirements of EU- Regulation No 10/211. This directive includes a limit of 10 mg/dm² on the overall migration from finished plastic articles into food. Please note that it is the responsibility of the industrial food packers to make sure that this article in its actual use is in compliance with the overall migration requirements.

Traceability:

FISCHER-PLASTIK has implemented appropriate systems and procedures that ensure traceability at all stages of production. Units of quantities are marked – usually with order confirmation numbers – in order to trace back the supply chain.

Usage

At room temperature resistant to inorganic acids (highly oxidizing excluded), bases, salts and their solutions, marginal swelling in case of contact with alcohol, fat, oil (of animal or vegetable origin) and wax possible.

The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

Storage: Store the product in dry storehouses at temperatures below 50°C. Polyethylene should not be exposed to UV radiation. FISCHER-PLASTIK does not take responsibility for any damages caused by adverse storage. Storable at least for eight months.

FISCHER-PLASTIK Ges.m.b.H.

Place and Date of issue
Allhaming 15/04/2016

*This document is created electronically and is valid without signature
Validity: 12 months*